



Made exclusively for NEMEON Members by APOC

PROFESSIONAL-GRADE PRODUCTS

LionGUARD Asphalt Primer

COMPLIANCE

Exceeds performance requirements of ASTM D41. MIAMI-DADE APPROVED. ASBESTOS FREE.

PRODUCT DESCRIPTION

LionGUARD Asphalt Primer is a professional grade primer formulated with a high penetrating solvent and select asphalt. It is designed to promote superior adhesion of roofing materials. LionGUARD Primer can be used to prime newly laid concrete or cement decks, gypsum, masonry thermal insulation and weathered roofing prior to applying built-up roofing. LionGUARD Primer can also be applied to weathered roofing prior to application of black or reflective coatings. Allow primer to cure 30 days prior to application of reflective coatings.

PREPARATION

All surfaces must have proper drainage and be clean, dry and free of surface rust and any other foreign matter. Repair all problem areas with an approved Lion Guard Cement. MIX THOROUGHLY. DO NOT HEAT OR THIN. DO NOT APPLY IF RAIN IS EXPECTED WITHIN 24 HOURS.

FOR BEST RESULTS

Apply on clear sunny day when surface temperatures are between 35 °F and 120 °F. In colder weather product should be stored in heated room (65 °F to 80 °F) at least 24 hours prior to application.

APPLICATION

For exterior use only. Protective clothing, gloves and eyewear should be used during application of these products. Apply with professional airless sprayer, brush or roller.

APPLICATION RATE

0.25 - 1 gallon per 100 sq. ft. depending on porosity of surface and method of application. Work material to a smooth and even consistency. Avoid excessive build up or puddles of primer. DO NOT APPLY TO ASPHALT DRIVEWAYS.

SPRAY INFO

100-500 PSI, .019-.031 Tip Size, 0.5 - 2.0 GPM

CLEAN UP

Clean tools with paint thinner or mineral spirits.



PRODUCT SPECIFICATIONS

Weight Per Gallon	7.4 - 7.9 lbs.
Residue by Evaporation, %	60 min.
Application Tool	Brush or Spray
Tack Time (50% Relative Humidity, 70 °F)	30 minutes
Full Cure (50% Relative Humidity, 70 °F)	24 - 48 hours
Application Temperatures	35 °F - 120 °F
Clean-up Tools	Paint Thinner, Mineral Spirits

Approx. Shipping Weights: (Note: all approx. weights include container)

5 gallons (18.9L)	40 lbs.
-------------------	---------

STORAGE & HANDLING PRECAUTIONS

When transporting this product, ensure that lid is tight and pail secure and upright. Do not allow pail to tumble as this may cause lid to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. Do not store at temperatures above 110 °F. This manufacturer also disclaims liability for flat surface application where poor drainage or moisture may prevail.

NEMEON, Inc. | 6043 Hudson Rd. Suite 350 Woodbury, MN 55125
Phone: (651) 788-7810 Fax: (651) 788-7807 | www.nemeon.com

APOC | 5903 Paramount Blvd, Long Beach, CA 90805
Phone: 1-800-562-5669 | www.apoc.com

